

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-157954

(43)Date of publication of application : 17.06.1997

(51)Int.Cl. D01F 8/14
C08L 67/04
C08L 67/04
D01D 5/30
D01F 1/09

(21)Application number : 07-316909 (71)Applicant : SHIMADZU CORP
KANEBO LTD

(22)Date of filing : 05.12.1995 (72)Inventor : MATSUI MASAO
KOSEKI HIDEKAZU
KONDO YOSHIKAZU
KAJIYAMA HIROSHI

(54) ANTISTATIC FIBER

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain antistatic fiber useful as clothing, etc., excellent in natural degradation and fiber performance, slightly polluting an environment, by combining a prescribed antistatic polymer with a specific fiber-forming polymer in a single fiber.



SOLUTION: This antistatic fiber is obtained by combining (A) an antistatic polymer 1 which is obtained by mixing (i) a polymer consisting essentially of an aliphatic polyester such as a polyglycolic acid with (ii) one or more compounds selected from the group consisting of a surfactant containing both a lipophilic

group and a hydrophilic group, a 2-4C alkyl group-containing polyalkylene ether and a derivative of the polyalkylene ether and has $\leq 1 \times 10^{11} \Omega \cdot \text{cm}$ volume resistivity with (B) a fiber-forming polymer 2 consisting essentially of an aliphatic polyester in a single fiber. The combining ratio (volume ratio) of the antistatic polymer 1 and the fiber-forming polymer 2 is preferably 10/90 to 60/40.